


SITEDRAIN™ SHEET 113

PREFABRICATED SHEET DRAIN



PRODUCT OVERVIEW

SITEDRAIN Sheet 113 geocomposite drain is composed of a dimpled polymeric core with a nonwoven geotextile bonded to the dimple side. The geotextile allows water to pass through while retaining backfill materials. The solid core allows water collection from one side and provides a continuous flow path to designated drainage exits.

SITEDRAIN Sheet 113 is an economical solution for single-sided subsurface drainage applications requiring moderate strength and high flow capacity.

PROPERTY ¹	TEST METHOD	UNIT OF MEASURE	Typical Value	MARV
GEOTEXTILE				
Material ²			PP, NPNW	PP, NPNW
Survivability	AASHTO M288	Class	-	-
Grab Tensile Strength	ASTM D4632	lbs	100	80
		N	445	356
Grab Elongation	ASTM D4632	%	70	50
CBR Puncture	ASTM D6241	lbs	305	210
		N	1,356	934
Trapezoidal Tear	ASTM D4533	lbs	50	30
		N	222	133
UV Resistance	ASTM D4355	% / 500 Hrs	70	70
Apparent Opening Size (AOS) ³	ASTM D4751	sieve	70	50
		mm	0.212	0.300
Permittivity	ASTM D4491	sec ⁻¹	2.7	2.2
Water Flow Rate	ASTM D4491	gpm / ft ²	165	150
		Lpm / m ²	6,724	6,112
CORE				
Compressive Strength	ASTM D6364 ASTM D1621	psf	11,000	-
		kPa	527	-
Thickness	ASTM D5199	in	0.4	-
		mm	10	-
In-Plane Flow Rate ⁴	ASTM D4716	gpm/ft	18	-
		Lpm/m	224	-
COMPOSITE				
Available Roll Sizes	Dimensions (ft)	Weight (lbs)	AWD Item Code	
	4 x 50	38	10000	

¹ Unless otherwise noted, all physical and performance properties listed are Typical Value or Minimum Average Roll Value (MARV) as defined in ASTM D4439.

² PP = Polypropylene; NPNW = Needle-Punched Nonwoven; WM = Woven Monofilament; SBNW = Spunbonded Nonwoven

³ Values for AOS represent Maximum Average Roll Value (MaxARV).

⁴ In-plane flow rate measured at 3,600 psf (172 kPa) compressive load and a hydraulic gradient of 1.0.

All technical information contained in this document is accurate as of publication. AWD reserves the right to make changes to products and literature without notice. Please refer to our website for the most current technical information available.